

CL3000 2V 3000Ah(10hr)

The rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and plates and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.



Battery Construction


Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

General Features

- Absorbent Glass Mat (AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.

Dimensions and Weight

Length(mm / inch).....710 / 27.95
 Width(mm / inch).....350 / 13.78
 Height(mm / inch).....345 / 13.58
 Total Height(mm / inch).....382 / 15.04
 Approx. Weight(Kg / lbs).....204 / 449.7



Performance Characteristics









Nominal Voltage2V
 Number of cell1
 Design Life20 years
 Nominal Capacity 77°F(25°C)
 10 hour rate (300A, 1.8V)..... 3000Ah
 5 hour rate (540A, 1.75V)..... 2700Ah
 1 hour rate (1860A, 1.6V)..... 1860Ah
 Internal Resistance
 Fully Charged battery 77°F(25°C)..... 0.08mOhms
 Self-Discharge
 3% of capacity declined per month at 20°C(average)
 Operating Temperature Range
 Discharge -20~60°C
 Charge -10~60°C
 Storage -20~60°C
 Max. Discharge Current 77°F(25°C)7000A(5s)
 Charge Methods: Constant Voltage Charge 77°F(25°C)
 Cycle use 2.35-2.45V
 Maximum charging current 600A
 Temperature compensation.....-5.0mV/°C
 Standby use 2.25-2.3V
 Temperature compensation.....-3.3mV/°C

Discharge Constant Current (Amperes at 77°F25°C)

End Point Volts/Cell	10min	15min	30min	45min	1h	3h	5h	10h
1.60V	5165	4033	2989	2173	1860	836	582	321
1.65V	4896	3839	2857	2086	1803	809	570	318
1.70V	4617	3639	2720	1994	1747	785	560	313
1.75V	4331	3436	2579	1898	1688	750	540	307
1.80V	4041	3230	2434	1800	1642	717	530	300

Discharge Constant Power (Watts at 77°F25°C)

End Point Volts/Cell	10min	15min	30min	45min	1h	2h	3h	5h
1.60V	7748	6050	4484	3477	2976	2040	1423	922
1.65V	7344	5759	4286	3338	2895	2017	1386	906
1.70V	6926	5459	4088	3199	2814	1942	1346	888
1.75V	6497	5154	3890	3060	2733	1859	1302	869
1.80V	6062	4845	3692	2921	2652	1770	1268	826



ISO9001:2000

MH25860

G4M19906-9202-E-16

www.vision-batt.com

Shenzhen Center Power Tech. Co., Ltd.
 Center Power Industrial Park, Tongfu Industrial District Dapeng Town, 518120 Shenzhen, China
 Tel: (+86-755) 8431 8088 Fax: (+86-755) 8431 8038 E-mail: sales@vision-batt.com